In the Claims

1. (Currently Amended) A sacrificial silicon-containing layer etching composition, comprising a-supercritical CO₂ (SCCO₂) fluid (SCF), at least one co-solvent, at least one etchant species, and at least one surfactant, wherein the etchant species comprises at least one bifluoride compound selected from the group consisting of ammonium bifluoride and tetraalkylammonium bifluoride ((R)₄NHF₂), wherein R is a C₁-C₄ alkyl group.

- 2. (Cancelled)
- 3. (Cancelled)
- 4. (Previously Presented) The composition of claim 1, wherein the co-solvent comprises at least one C_1 - C_6 alcohol.
- 5. (Previously presented) The composition of claim 1, wherein the co-solvent comprises methanol.
- 6. (Previously presented) The composition of claim 1, wherein the co-solvent comprises isopropanol.
- 7. (Previously presented) The composition of claim 1, wherein the sacrificial siliconcontaining layer comprises silicon oxide.
- 8. (Cancelled)
- 9. (Previously presented) The composition of claim 1, wherein the etchant species comprises ammonium bifluoride.
- 10. (Cancelled)

- 11. (Previously Presented) The composition of claim 1, wherein the surfactant is selected from the group consisting of fluoroalkyl surfactants, polyethylene glycols, polypropylene polyethylene ethers, polypropylene glycol ethers, carboxylic acid salts, dodecylbenzenesulfonic acid, dodecylbenzenesulfonic salts, polyacrylate polymers, dinonylphenyl polyoxyethylene, silicone polymers, modified silicone polymers, acetylenic diols, modified acetylenic diols, alkylammonium salts, modified alkylammonium salts, and combinations comprising at least one of the foregoing.
- 12. (Previously presented) The composition of claim 11, wherein the surfactant comprises a modified acetylenic diol.
- 13. (Currently Amended) The composition of claim 11, wherein the etching composition comprises about 75.0 wt % to about 99.5 wt % SCCO₂ SCF, about 0.3 wt % to about 22.5 wt % co-solvent, about 0.01 wt % to about 5.0 wt % etchant species, and about 0.01 wt % to about 5.0 wt % surfactant, based on the total weight of the composition.
- 14. (Previously presented) The composition of claim 1, wherein the sacrificial siliconcontaining layer consists essentially of silicon.

15.-16. (Cancelled)

- 17. (Withdrawn) A method of removing silicon-containing substances from a substrate having same thereon, said method comprising contacting the substrate with a SCF-based composition comprising $\underline{SCCO_2}$ a SCF, at least one co-solvent, at least one etchant species, and optionally at least one surfactant, for sufficient time and under sufficient contacting conditions to remove the silicon-containing substances from the substrate, wherein the etchant species comprises at least one bifluoride compound selected from the group consisting of ammonium bifluoride and tetraalkylammonium bifluoride ((R)₄NHF₂), wherein R is a C₁-C₄ alkyl group.
- 18. (Cancelled)
- 19. (Cancelled)

- 20. (Withdrawn) The method of claim 17, wherein the contacting conditions comprise pressures in a range of from about 1400 to about 4400 psi.
- 21. (Withdrawn) The method of claim 17, wherein said contacting time is in a range of from about 30 seconds to about 30 minutes.
- 22. (Withdrawn) The method of claim 17, wherein the co-solvent comprises at least one C₁-C₆ alcohol.
- 23. (Withdrawn) The method of claim 17, wherein the co-solvent comprises methanol.
- 24. (Withdrawn) The method of claim 17, wherein the co-solvent comprises isopropanol (IPA).
- 25. (Withdrawn) The method of claim 17, wherein the silicon-containing substance comprises a sacrificial silicon oxide layer.
- 26. (Cancelled)
- 27. (Withdrawn) The method of claim 17, wherein the etchant species comprises ammonium bifluoride.
- 28. (Cancelled)
- 29. (Withdrawn) The method of claim 17, wherein the surfactant is selected from the group consisting of fluoroalkyl surfactants, polyethylene glycols, polypropylene glycols, polyethylene ethers, polypropylene glycol ethers, carboxylic acid salts, dodecylbenzenesulfonic acid, dodecylbenzenesulfonic salts, polyacrylate polymers, dinonylphenyl polyoxyethylene, silicone polymers, modified silicone polymers, acetylenic diols, modified acetylenic diols, alkylammonium salts, modified alkylammonium salts, and combinations comprising at least one of the foregoing.

- (Withdrawn) The method of claim 29, wherein the etching composition comprises about 75.0 wt % to about 99.5 wt % SCCO₂ SCF, about 0.3 wt % to about 22.5 wt % co-solvent, about 0.01 wt % to about 5.0 wt % etchant species, and about 0.01 wt % to about 5.0 wt % surfactant, based on the total weight of the composition.
- 31. (Withdrawn) The method of claim 17, wherein the silicon-containing substance is selected from the group consisting of silicon, post-ash residue and post-etch residue.
- 32. (Cancelled)
- 33. (Withdrawn) The method of claim 31, further comprising dehydrating the substrate prior to contacting the substrate with the SCF-based etching composition.
- 34. (Cancelled)
- 35. (Withdrawn) The method of claim 17, wherein the contacting step comprises a etching cycle including (i) dynamic flow contacting of the etching composition with the silicon-containing substance, and (ii) static soaking contacting of the etching composition with the silicon-containing substance.
- 36. (Withdrawn) The method of claim 35, wherein said etching cycle comprises alternatingly and repetitively carrying out dynamic flow contacting (i) and static soaking contacting (ii) of the silicon-containing substance.
- 37. (Withdrawn) The method of claim 17, further comprising the step of washing the substrate, at a region at which the silicon-containing substance has been removed, with a SCF/methanol/deionized water wash solution in a first washing step, and with a SCF in a second washing step, to remove residual precipitated chemical additives in said first washing step, and to remove residual precipitated chemical additives and/or residual alcohol in said second washing step.

- 38. (Withdrawn) The method of claim 37, wherein the SCF is SCCO₂.
- 39. (New) A sacrificial silicon-containing layer etching composition consisting essentially of supercritical CO₂ (SCCO₂), at least one co-solvent, and at least one bifluoride compound selected from the group consisting of ammonium bifluoride and tetraalkylammonium bifluoride ((R)₄NHF₂), wherein R is methyl, ethyl, butyl, phenyl or fluorinated C₁-C₄ alkyl groups.
- 40. (New) A sacrificial silicon-containing layer etching composition consisting of supercritical CO₂ (SCCO₂), at least one co-solvent, and at least one bifluoride compound selected from the group consisting of ammonium bifluoride and tetraalkylammonium bifluoride ((R)₄NHF₂), wherein R is methyl, ethyl, butyl, phenyl or fluorinated C₁-C₄ alkyl groups.